

# ASTM G21-15

## *Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi*

*FINAL REPORT: R2021-296-1*

Prepared for:  
Caesarstone  
Kibbutz Sdot-Yam MP  
Menashe 37804, Israel

*Accredited Testing Provided by:*



130 Erick Street  
Crystal Lake, IL 60014  
815.526.0954  
TESTING CERT: #2832.01

*Testing Initiated: April 22, 2021*  
*Testing Completed: May 20, 2021*  
*Report Issued: May 25, 2021*

Performed By: Agata Shulfer  
Title: Senior Staff Scientist

Approved By: Debbie Koester  
Title: Quality Manager



## **Objective:**

To evaluate the mold resistance properties of three samples as seen in the ASTM G21 fungal resistance test.

## **Test Sample Identification:**

Caesarstone Quartz:

1. 2003H Quartz
2. 2003P Quartz
3. 4033RC Quartz

## **Test Procedure Summary:**

Samples are placed onto the surface of ASTM G21 nutrient salts agar and sprayed with a mixed spore suspension of five fungal strains. The nutrient salts agar provides all of the trace nutritional elements needed by fungi to support growth. However, to achieve a heavy growth, the fungi must use the test material as its primary carbon source. Inoculated samples are incubated and then examined for fungal growth.

### Test Variables

<b>Test Organisms:</b>	<i>Aspergillus brasiliensis</i> <sup>1</sup>	ATCC 9642
	<i>Talaromyces pinophilus</i> <sup>2</sup>	ATCC 11797
	<i>Chaetomium globosum</i>	ATCC 6205
	<i>Trichoderma virens</i> <sup>3</sup>	ATCC 9645
	<i>Aureobasidium pullulans</i>	ATCC 15233

---

**Sample Description:** 2" x 2" pieces

---

**Test Surface:** Polished side

---

**Number of Replicates per Sample:** Three

---

**Positive Growth Control:** Sterile Filter Paper

---

**Media Used:** Nutrient-Salts Agar prepared according to standard

---

**Environmental Conditions:** 28 - 30°C; ≥85% relative humidity

---

**Incubation Duration:** 28 days

---

**Deviations from Standard Test Method:** None, testing performed per ASTM G21 without deviation.

<sup>1</sup> *Aspergillus brasiliensis* formerly classified as *Aspergillus niger*

<sup>2</sup> *Talaromyces pinophilus* formerly identified as *Penicillium funiculosum*

<sup>3</sup> *Trichoderma virens* formerly classified as *Gliocladium virens*



## **Results:**

The results for the test pieces can be found in the data table below. The filter paper control pieces had copious fungal growth at Day 14. Temperature and relative humidity were maintained for the duration of the test. These results pertain only to the samples tested.

At week 4, samples rating a “0” or “1” were examined microscopically to confirm the ratings.

The rating scale for this test is as follows:

<b>Rating</b>	<b>Observed Growth</b>
0	No Growth
1	Trace of Growth (less than 10% coverage)
2	Light Growth (10-30% coverage)
3	Medium Growth (30-60% coverage)
4	Heavy Growth (60-100% coverage)

<b>Sample Identification</b>	<b>Rep</b>	<b>Week 1</b>	<b>Week 2</b>	<b>Week 3</b>	<b>Week 4</b>
Caesarstone Quartz 2003H Quartz	1	0	0	0	0
	2	0	0	0	0
	3	0	0	0	0
Caesarstone Quartz 2003P Quartz	1	0	0	0	0
	2	0	0	0	0
	3	0	0	0	0
Caesarstone Quartz 4033RC Quartz	1	0	0	0	0
	2	0	0	0	0
	3	0	0	0	0